



**9A**  
**SOLID FILM LUBRICANT: HEAT CURE**  
**SERIES E750**  
 QUALIFIED TO SAE AS5272 Type II  
 (FORMERLY MIL-L- 46010D Type II)

**SANDSTROM**  
**PRODUCTS COMPANY**  
 PORT BYRON, IL 61275 • 1-309-523-2121  
 1-800-747-1084 • FAX: 1-309-523-3912  
[www.sandstromproducts.com](http://www.sandstromproducts.com)

**DESCRIPTION**

Sandstrom 9A dry film lubricant is a paint-like coating containing molybdenum disulfide and corrosion inhibiting pigments. This heat curing material prevents corrosion, galling, seizing and fretting. It is a low-friction coating which exhibits long wear life when operated at -320°F to +500°F under loads exceeding 100,000 psi. Sandstrom 9A should be applied where maximum wear life and corrosion protection from a dry film lubricant are required.

Sandstrom 9A may be applied by brush, dip or spray method to a wide variety of surfaces. After it is heat cured, 9A is virtually unaffected by atmospheric and fretting corrosion, solvents, acids, oils or degreasers and is not re-softened at elevated temperatures.

Basic Product Guidance:

- Use LC-300 or #099 on metals that may be adversely affected by a 1 hour @ 400°F bake cycle.
  - Use 9A on metals not affected by higher bake temperatures.
  - Use #099 to meet low VOC requirements.
- Please consult Sandstrom Technical Rep during product selection process for best results.

**OUTSTANDING FEATURES/BENEFITS**

- Excellent Corrosion Protection
- Chemical Resistance
- Long Wear Life
- **9A CONTAINS NO GRAPHITE**

**NOTICE**

**Before using this product, read all warnings, limitations and safety information printed on the product label, Safety Data Sheet (MSDS), and Technical Data Sheet.**

**TYPICAL USES**

Sandstrom 9A is an excellent solution to the problem of lubricating parts:

- That will be operated in corrosive atmospheres.
- That may be stored for long periods.
- That are seldom lubricated once they leave the factory and permanent lubrication is desired.
- Where operating pressures exceed the load-bearing capacities of ordinary oils and greases.
- Where "clean operation" is desired (does not collect dirt and debris like grease and oils).
- Where a protective coating and sacrificial break-in lubricant is needed.
- Where fretting and galling is a problem (e.g., splines, universal joints, keyed bearings).
- Where easy release is desired (e.g., fasteners, PVC molds).
- Where parts may be subjected to frequent disassembly.

**LIMITATIONS**

Do not use 9A where there is potential for contact with liquid oxygen or food.

COMPOSITION AND PHYSICAL PROPERTIES			
Net Weight per gallon <i>ASTM D1475</i>	9.5 lbs. ± 0.2 lbs.	Vehicle	Epoxy-Phenolic
Weight Solids	40% minimum	Lubricating Pigment	Molybdenum Disulfide
VOC – water	5.5578 lbs./gallon (Theoretical)	Color	Flat Dark Gray
Odor	Strong Solvent	Cleanup	See CLEANUP
Viscosity	40-46 seconds, #1 EZ Zahn cup @ 77°F	Thinner	See THINNING
Shelf Life	1 year from date of manufacture	Coverage Rate *	660 sq. ft./gal @ 0.5 mil DFT
Storage Conditions	≤ 100°F	Recommended Coats	1
Flash Point	23° ± 2°F Setaflash	Dry Film Thickness	0.5 mil

\* Actual figures do not include spray loss. Also allow for surface irregularities and porosity, as well as material loss when mixing.

PERFORMANCE AND FUNCTIONAL PROPERTIES			
Coefficient of Friction	0.0236 (Falex Test)	LOX Capability	100% compatible & shock resistant
Corrosion Protection:		Operating Temperature Range	-320°F to +500°F
<i>ASTM B117: Steel MIL-DTL-16232 Type M Class 3</i>	> 1500 hours * (at 0.5 mil)	Resistivity	1.4 x 10 <sup>6</sup> Ohms CM
Fluid Resistance:		Thermal Stability	Pass
<i>SAE AS5272 Table 3 Fluids</i>		<i>ASTM D2511</i>	
<i>ASTM D2510 C</i>	Pass	Vacuum Outgassing	None @ 10 <sup>-6</sup> Torr.
Load Carry Capacity	2250 lbf	Wear Life	496 minutes average
<i>ASTM D2625B</i>		<i>ASTM D2625A</i>	

\* Tests halted before failure.

IMPORTANT NOTICE TO BUYER / WARRANTY AND LIMITATIONS ON OUR LIABILITY  
 We warrant our products to be free of manufacturing defects and that they meet our current published physical properties and specifications. All information and suggestions presented are rendered gratis and are accurate to the best of our knowledge. They are based on technical data we believe to be reliable and are intended for use by persons having skill and "know-how" at their own discretion and risk. Prior to use, customers are cautioned to determine the suitability of our products for any given application through their own testing. NO WARRANTY IS MADE, EXPRESS OR IMPLIED, REGARDING SUCH INFORMATION, THE DATA ON WHICH IT IS BASED OR THE RESULTS OBTAINED FROM ITS USE OR THAT OUR PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE. SUCH STATEMENTS ARE NOT INTENDED TO SUGGEST INFRINGEMENT OF ANY PATENT. Since conditions of use of our products are beyond our control, all suggestions and statements are made without guarantee, warranty or other responsibility, express or implied, on our part. We assume no responsibility for results obtained, or damages incurred, from their use beyond replacing material proved to be defective or refunding the purchase price of such material at our option. Acceptance of delivery of our product means you have accepted the terms of this warranty, whether or not purchase orders of other documents state terms that vary from this warning. No seller is authorized to make any representations or warranty or assume any other liability on our behalf with any sales of our products. SANDSTROM PRODUCTS COMPANY

**GENERAL**

Sandstrom 9A is a paint-like material consisting of lubricative pigments dispersed in a thermosetting resin system thinned with appropriate solvents. For maximum service, the APPLICATION INSTRUCTIONS MUST BE FOLLOWED CLOSELY.

**FILM THICKNESS & ENGINEERING TOLERANCE**

As supplied, Sandstrom 9A will yield a film thickness of about 0.0005 inches per dip coat. Usually engineering tolerances will permit necessary minimum film buildup of 0.0002 to 0.0003 inches without interference. If excess buildup does occur and a force fit is necessary, burnishing lightly will assist in mating the parts. The remaining excess will be worn away in the first few cycles of operation. Whenever possible, the proper tolerances should be designed into the part.

**COVERAGE**

One gallon of this material will cover 660 sq. ft. with a dry film thickness of 0.0005 inches. Coverage depends upon methods of application and other variables such as overspray and type of surface to be coated. Above coverage rates are based on 100% efficiency.

**SURFACE PREPARATION**

Please contact Sandstrom Products Company for substitute surface preparations if recommended steps cannot be followed.

**Application on steel.** Pre-clean surface with aliphatic naphtha or any other EPA compliant cleaner that sufficiently cleans surface to pass ASTM F22. Abrasive blast surface with 180-220 grit aluminum oxide (25-50 RMS optimum). Phosphate IAW MIL-DTL-16232 (weight should be 11-22 g/m<sup>2</sup>), type M, class 3 (optimal performance) or type Z, class 3.

**Application on stainless steels.** Pre-clean surface with aliphatic naphtha or any other EPA compliant cleaner that sufficiently cleans surface to pass ASTM F22. Abrasive blast surface with 180-220 grit aluminum oxide (25-50 RMS optimum). Passivate surface with ASTM A967, types nitric 1, nitric 2 or nitric 3, as applicable.

**Application on aluminum and aluminum alloys.** Pre-clean surface with aliphatic naphtha or any other EPA compliant cleaner that sufficiently cleans surface to pass ASTM F22. Sulfuric acid anodize IAW MIL-A-8625 and seal surface.

**Application on titanium and titanium alloys.** Degrease surface to be coated with aliphatic naphtha or any other EPA compliant cleaner that sufficiently cleans surface to pass ASTM F22. Abrasive blast surface with 180-220 grit aluminum oxide (25-50 RMS optimum) and alkaline anodize.

**Application on copper and copper alloys.** Pre-clean surface with aliphatic naphtha or any other EPA compliant cleaner that sufficiently cleans surface to pass ASTM F22. Abrasive blast surface with 180-220 grit aluminum oxide (25-50 RMS optimum). Form a black oxide finish on surface.

**STIRRING**

**IMPORTANT! THIS LUBRICANT CONTAINS HEAVY PIGMENTS WHICH SETTLE RAPIDLY. THEREFORE, IT SHOULD BE STIRRED THOROUGHLY BEFORE USE AND CONTINUOUSLY DURING APPLICATION.**

**THINNING**

**For brushing** – Use as supplied.

**For spraying** \* - Use 2 parts 9A to 1 part PM solvent (Sandstrom D106 Thinner).

**For dipping** \* - Use slow-drying thinner mixture of PM and PMA, blended 1:1 (Sandstrom D122 Thinner), as to provide proper run-off characteristics. The suggested starting point is 4 parts 9A to 1 part thinner mixture.

\* By volume.

**APPLICATION**

***For Spec work, follow all instructions in the drawing.***

Sandstrom 9A may be brushed, sprayed or dipped to the desired film thickness (usually 0.0003 to 0.0007 inches). Allow parts to flash off **at least 30 minutes at 77°F ± 5°F and ≤ 70%** relative humidity. Lower temperatures and/or higher humidity may require a longer dry time to prevent film defects.

It is important to keep container closed when not in use to keep loss of solvents at a minimum and avoid a change in volume solids.

**BAKING**

Bake for 1 hour @ 400°F in a forced draft oven to yield optimum corrosion protection and wear life.

**IMPORTANT!** The hour begins when **the part** has reached 400°F, NOT when it is placed in the Class A oven. In cases of very thick metals, an extra hour may be required to bring the part up to the proper temperature. Thermocouples may be used to determine the true temperature of the metal. However, if the metallurgical properties are adversely affected by baking at this temperature (i.e., ALUMINUM, in some cases), we recommend use of Sandstrom LC-300, which cures for 1 hour at 300°F (149°C). Sandstrom #099 could also be used, as it cures in temperatures ranging from 300°F to 400°F.

**IT IS IMPERATIVE TO USE A PROPERLY VENTED OVEN (DIRECT VENT TO THE OUTSIDE).**

**CLEANUP**

Use the same solvents for cleaning tools as are recommended for thinning.

**REMOVAL**

In the event it is necessary to remove Sandstrom 9A, physical removal is best (such as grit blasting, sanding, or grinding).

**WARNINGS:** Constant stirring is imperative for best results.

**DANGER! USE WITH ADEQUATE VENTILATION.**

\*\*\*Strict compliance to the instructions given in Surface Preparation, Thinning, Application, and Baking is very essential for obtaining optimum results.\*\*\*

**IMPORTANT! DO NOT TOUCH CLEAN SURFACE WITH FINGERS - OIL FROM THE HANDS WILL INTERFERE WITH PROPER COATING ADHESION.** Whenever possible, treat both contact surfaces (i.e., the shaft and the bearing).

**IMPORTANT NOTICE TO BUYER / WARRANTY AND LIMITATIONS ON OUR LIABILITY**

We warrant our products to be free of manufacturing defects and that they meet our current published physical properties and specifications. All information and suggestions presented are rendered gratis and are accurate to the best of our knowledge. They are based on technical data we believe to be reliable and are intended for use by persons having skill and "know-how" at their own discretion and risk. Prior to use, customers are cautioned to determine the suitability of our products for any given application through their own testing. NO WARRANTY IS MADE, EXPRESS OR IMPLIED, REGARDING SUCH INFORMATION, THE DATA ON WHICH IT IS BASED OR THE RESULTS OBTAINED FROM ITS USE OR THAT OUR PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE. SUCH STATEMENTS ARE NOT INTENDED TO SUGGEST INFRINGEMENT OF ANY PATENT. Since conditions of use of our products are beyond our control, all suggestions and statements are made without guarantee, warranty or other responsibility, express or implied, on our part. We assume no responsibility for results obtained, or damages incurred, from their use beyond replacing material proved to be defective or refunding the purchase price of such material at our option. Acceptance of delivery of our product means you have accepted the terms of this warranty, whether or not purchase orders of other documents state terms that vary from this warning. No seller is authorized to make any representations or warranty or assume any other liability on our behalf with any sales of our products. SANDSTROM PRODUCTS COMPANY